




# PHYSICAL PERFORMANCE PROPERTIES

## AMES® BLOCK & WALL™



Ames' Block & Wall is an elastomeric waterproofing sealant for exterior, above-grade walls. Block & Wall dries to form a waterproof seal to keep water and moisture out. This product expands and contracts up to 700%, is highly resistant to cracking and peeling, and remains flexible at -35°F. Block & Wall is ideal for block walls, basement walls, stucco and many other surfaces. It is heavy duty, yet easily applied by brush, roller or sprayer. Cleans easily with water.

Appearance (cured).....	Rubberized plastic coating
Appearance (liquid).....	Thick, white liquid
Color.....	Tintable white ( Ames Block & Wall may be tinted to pastel colors using universal latex colorants)
Solar Reflectance.....	Up to 98%
Mildew resistance.....	Excellent
Weight.....	Approx. 11 pounds/gallon
Solvent.....	Water
Odor.....	Mild
Permeability.....	Less than one perm with 30 mils/min. of coating
Elongation.....	Up to 700%
Strength.....	250 PSI
Viscosity.....	12,000 cps spdl. #7/100 RPM
PH as shipped.....	9.5 - 10
Specific Gravity.....	1.10
Freeze/Thaw Stability Test of dried material.....	At -35 degrees F, Ames Block & Wall passes 180 degree bend test. If frozen while in liquid form, the product may be rendered unusable.
Setting time.....	30 min. - 1 hour at 50° -100° F. at less than 30% humidity
Cure time.....	Approximately 2 to 8 hours at 50° to 100° F. at less than 30% humidity
Material composition.....	Waterbase elastomeric rubberized plastic
Toxicity.....	Non-toxic when dry
Flash point.....	1800° C
Fire rating.....	Class "A" ASTM E-108. over AC. ASTM E-84 zero smoke
Coverage rate.....	Approx. 100 square feet per gallon
Voc Content.....	Less than 1 gram per liter

Formulas have been tested in accordance with ASTM E 108 E-108 Class "A" over AC.ASTM E-84 zero smoke, zero ignition. **Important:** Apply a small amount to ensure the product performs satisfactorily.

Ames Research Laboratories, Inc., PO Box 1350 Jefferson, OR USA 97352

Toll-Free: 1-888-345-0809 • Phone: 503-588-3330 • Fax: 503-364-2380 • www.amesresearch.com • amesstaff@amesresearch.com