





PHYSICAL PERFORMANCE PROPERTIES



Ames Research Laboratories, Inc., PO Box 1350 Jefferson, OR USA 97352
 Toll-Free: 1-888-345-0809 • Phone: 503-588-3330 • Fax: 503-364-2380
www.amesresearch.com • amesstaff@amesresearch.com



ELASTO-BARRIER

Appearance (cured).....	Liquid Rubber.
Appearance (liquid).....	Thick, Creamy
Color.....	Gray
Mildew resistance.....	Excellent
Weight.....	Approx. 11 Pounds/gallons
Solvent.....	Water
Odor.....	Mild
Permeability.....	Less than one perm in one coat.
Elongation.....	up to 1000%.
Strength.....	250+ psi when heavy duty Polyester Contouring Roof Fabric is used.
Viscosity.....	4050 cps spdl. # 7.100 rpm
PH as shipped.....	10.4 - 11
Specific Gravity.....	1.10
Bonding.....	Bonds to most surfaces including tar, metal and rolled roofing. Does not bond to wax base surfaces.
Freeze/Thaw Stability Test of dried material.....	At -35° F, Elasto-Barrier passes 180 degree bend test. Elasto-Barrier, if frozen while in liquid form, may be damaged or solidify. Protect from freezing.
Setting time.....	15 min. -1 hour at 40° - 80° F. at less than 30% humidity.
Cure time.....	At 40° - 80° F. 2 to 8 hours. When roofing fabric is embedded allow 24 hours total curing.
Material composition.....	A sophisticated copolymer/polymer based on rubber chemistry.
Toxicity.....	Non-toxic after curing.
Flash point.....	1500° F. (estimated)
Fire rating.....	ASTM E-108 Class "A" over AC. ASTM E-84 zero smoke.
Tukon Hardness (KHN).....	Less than one.
Coverage rate.....	Approx. 100 square feet per gallon.
Voc Content.....	Less than 1 gram per liter.

Formulas have been tested in accordance with ASTM E 108 E-108 Class "A" over AC. ASTM E-84 zero smoke, zero ignition.

Special Comments: Do not thin with water more than 2%. Excessive thinning will solidify product.

Applications: Tar and metal roofs, basements walls, below and above grade water protection over plywood and concrete.

Important: Apply a small amount to ensure the product performs satisfactorily.